

Material Data Sheet

GC pro 3560 TH 060 N

Easy flowing PP-Compound with 35 wt% natural fibers derived from sunflower seed hulls.

Fibers derived from sunflower seed hulls are a side product of sunflower oil production. They are GMO free, do not compete with the foodchain and do not require additional areal. Golden Compound pro has a lower carbon footprint than the materials it is targeted to replace.

Mechanical Properties

<i>Property</i>	<i>Norm</i>	<i>Units</i>	<i>Value</i>
Density	ISO 1183	g/cm ³	1.02
MVR	ISO 1133 (190 °C/5 kg)	cm ³ /10 min	40
E-Modulus	ISO 527	MPa	2400
Tensile Strength	ISO 527	MPa	28
Elongation at break	ISO 527	%	4.8
Flexural Modulus	ISO 178	MPa	2200
Flexural Strength	ISO 178	MPa	46
Flexural strain at break	ISO 178	%	6.2
Charpy unnotched _{23 °C}	ISO 179/1eU	kJ/m ²	11.5
Charpy notched _{23 °C}	ISO 179/1eA	kJ/m ²	2.2

Processing Guidelines

Melt Temperature	°C	180 - 190
Mold Temperature	°C	20 - 60
Drying Temperatur	°C	80
Drying Time	h	4
Maximum Moisture Content	%	0.04