

## Material Data Sheet

GC pro 3545 BO 10LP41

Easy flowing PP-Compound with 35 wt% natural fibers derived from sunflower seed hulls.

Fibers derived from sunflower seed hulls are a side product of sunflower oil production. They are GMO free, do not compete with the foodchain and do not require additional areal. Golden Compound pro has a lower carbon footprint than the materials it is targeted to replace.

### Mechanical Properties

<i>Property</i>	<i>Norm</i>	<i>Units</i>	<i>Value</i>
Density	ISO 1183	g/cm <sup>3</sup>	1.02
MVR	ISO 1133 (190 °C/5 kg)	cm <sup>3</sup> /10 min	33
E-Modulus	ISO 527	MPa	1700
Tensile Strength	ISO 527	MPa	22
Elongation at break	ISO 527	%	10.3
Charpy unnotched <sub>23 °C</sub>	ISO 179/1eU	kJ/m <sup>2</sup>	25.2
Charpy notched <sub>23 °C</sub>	ISO 179/1eA	kJ/m <sup>2</sup>	6.7

### Thermal Properties

HDT A	ISO 75-1 (1.8 MPa)	°C	111
-------	--------------------	----	-----

### Processing Guidelines

Melt Temperature	°C	180 - 190
Mold Temperature	°C	20 - 60
Drying Temperatur	°C	80
Drying Time	h	4
Maximum Moisture Content	%	0.04